



# Technical Data Sheet: CR91212

<b>Product manual</b>	<p><b>CR91212</b> is a polyester triacrylate oligomer with the characteristics of fast curing speed, good yellow resistance, good weather resistance and excellent adhesion. It can be used on wood coatings, plastic coatings and so on.</p>	
<b>Product features</b>	<p>Fast curing speed</p> <p>Good yellow resistance</p> <p>Good weather resistance</p> <p>Low odor</p>	
<b>Recommended use</b>	<p>Wood Coatings</p> <p>PVC</p>	
<b>Specifications</b>	Functionality (theoretical)	3
	Appearance (By vision)	Clear liquid
	Viscosity (CPS/25°C)	100000–150000
	Color (APHA)	≤100
	Efficient content (%)	100
	Acid Value (mgKOH/g)	≤10
<b>Packing</b>	<p>Net weight 50KG plastic bucket and net weight 200KG iron drum</p>	
<b>Storage conditions</b>	<p>Please keep cool or dry place, and avoid sun and heat;</p> <p>Storage temperature does not exceed 40 °C, storage conditions under normal conditions for at least 6 months.</p>	
<b>Use matters</b>	<p>Avoid touching the skin and clothing, wear protective gloves when handling;</p> <p>Leak with a cloth when the leak, and wash with ethyl acetate;</p> <p>for details, please refer to the Material Safety Instructions (MSDS);</p> <p>Each batch of goods to be tested before they can be put into production.</p>	