



Technical Data Sheet: HP6919		
Product manual	<b>HP6919</b> is an aliphatic urethane acrylateoligomer developed for UV/EB-cured coatings and inks. <b>HP6919</b> imparts hardness & toughness, very fast cure response, and nonyellowing characteristics to these applications.	
Product features	Non-yellowing Very fast cure Good Adhesion Good Hardness & toughness Good Weatherability High Abrasion Resistance Vibration resistance	
Suggested	Coatings	
application	Coatings, plastic Inks, flexo	
	Inks, litho	
Specifications	Functional basis (theoretical)	9
	Appearance(By vision)	Little yellow liquid
	Viscosity (CPS/60°C)	6000-14000
	Color (APHA)	≤ 100
	Efficient content(%)	100
Packing	Net weight 50KG plastic bucket and net weight 200KG iron drum.	
Storage conditions	Resin please keep cool or dry place, and avoid sun and heat; Storage temperature does not exceed 40 $^\circ$ C, storage conditions under normal conditions for at least 6 months.	
Use matters	Avoid touching the skin and clothing, wear protective gloves when handling; Leak with a cloth when the leak, and wash with ethyl acetate; for details, please refer to the Material Safety Instructions (MSDS); Each batch of goods to be tested before they can be put into production.	

TEL: 0769-83562087